



















TECHINICAL DATA SHEET

COLLECTION CLIVE
 COLOR: NATURAL, ARENA, GRIS, ANTRACITA
 FINISH: MATTE
 FORMAT: 60x60

	Test Standard UNE-EN ISO 10545	Product Standard ISO 13006-EN1441	DURSTONE VALUES	
Características dimensionales <i>Dimensional and Surface Appearance</i>				
	Espesor <i>Thickness</i>	ISO 10545-2	± 0,05%	Cumple/Achieved
	Longitud y anchura <i>Length and width</i>	ISO 10545-2	± 0,05%	Cumple/Achieved
	Ortogonalidad <i>Squareness</i>	ISO 10545-2	± 0,6%	Cumple/Achieved
	Planaridad <i>Surface Flatness</i>	ISO 10545-2	± 0,05%	Cumple/Achieved
Propiedades físicas <i>Physical properties</i>				
	Absorción de agua <i>Water absorption</i>	ISO 10545-3	≤ 0,5%	<0,5%
	Resistencia a flexión N/mm² <i>Modulus of rupture</i>	ISO 10545-4	≥ 35	≥ 36
	Carga de ruptura N <i>Breaking strength</i>	ISO 10545-4	≥ 1300	≥ 2800
	Resistencia a la abrasión superficial (PEI) <i>Resistance to surface abrasion (PEI)</i>	ISO 10545-7	-	4
	Resistencia al choque térmico <i>Resistance to thermal shock</i>	ISO 10545-9	Exigida/Required	Cumple/Achieved
	Resistencia a la helada <i>Frost resistance</i>	ISO 10545-12	Exigida/Required	Cumple/Achieved
	Resistencia al rayado (MOHS) <i>Scratch resistance (MOHS)</i>	UNE EN-101	-	-
	Deslizamiento <i>Antislip</i>	ENV 12633	-	CLASS 1
		DIN 51130	-	-
		ANSI A 137.1	>42	-
		BS7976-2	≥36	-
Propiedades químicas <i>Chemical properties</i>				
	Resistencia a productos de limpieza y aditivos <i>Resistance to household chemical ans swimming pool</i>	ISO 10545-13	Min. GB/UB	A
	Resistencia a ácidos y bases <i>Resistance to acids and alkalis (low concentration)</i>	ISO 10545-13	GLB/ULB	LA
	Resistencia a ácidos y bases <i>Resistance to acids and alkalis (high concentration)</i>	ISO 10545-13	GHB/UHB	HA
	Resistencia a las manchas <i>Resistance to staining</i>	ISO 10545-13	Min. 3	5